

INSTRUCTIONS FOR USE

For best results, depending on the mix used and the ambient temperature, workability will be retained for between 10 and 20 minutes. It is important that your product is made without prolonged mixing and is placed and fully compacted as soon as possible after mixing. (The amount of materials mixed in any one operation should be small enough to ensure that all the material can be used and the mixing equipment thoroughly cleaned out before the mix has set.) Note: The rapid setting nature of this product makes it unsuitable for large concrete slabs or large screed areas as they cannot normally be placed and finished in the available time.

STORAGE CONDITIONS AND SOLUBLE CHROMIUM (VI)

This product must be stored in unopened bags clear of the ground in cool dry conditions and protected from excessive draught. If stored correctly, as detailed above, the chromium (VI) in this product will be within required levels for up to 12 months from the date shown on the bag. Use of this product after the declared storage period, as detailed above, may increase the risk of an allergic reaction following direct contact with skin.

PACKAGING

Reader CemFast® comes in an easy to handle, fully waterproof all weather bag.

COVERAGE RATE

When mixed with water, 1200kg of Reader CemFast® will fill one cubic metre of area.

COMPRESSIVE STRENGTH

Approximately 40 Nmm² @ 28 days.

STORAGE

The product must be stored in unopened bags and is clear of the ground. If stored correctly the shelf life of the product if packed in fully water-proof plastic sacks is up to 12 months from the date shown on the bag.

If the product is used after declared storage period this may increase the risk of an allergic reaction following direct contact with the skin.

Packed into 100% waterproof bags, palletised and stretch hood covered.

Ideal for external storage.

SUPPLIED

Reader CemFast® can be supplied in bulk tanker loads, 20kg plastic bags or 1 tonne bags, palletised and shrink wrapped.

DESCRIPTION

Reader CemFast® is a Portland Cement containing calcium sulfo-aluminate and special additives, developed to give quick setting and hardening characteristics. At present there is no appropriate British Standard for this product.

Reader CemFast® is an ideal cement for repair and maintenance applications where the increased rate of set and strength development are beneficial in both mortar and concrete, allowing normal services to be brought back into operation after only a few hours.



APPLICATIONS

- Fixing manhole covers
- Fitting ridge tiles
- Concrete paths/steps
- Repairs and maintenance
- Internal or external applications

Reader Cement Products Ltd.

Kirkby Lane, Pinxton, Nottinghamshire, NG16 6HX, United Kingdom.

T: +44 (0)1623 518 350 E: info@reader.co.uk W: reader.co.uk

Issued January 2024 – Replaces all previous versions

Danger

Causes serious eye damage
Causes skin irritation

May cause allergic skin reaction
May cause respiratory irritation

